

DATA SHEET

LaNe[®] Fibre-Composite sheet black

1200x500x 0,8-1,0 mm - Art. 81 266

1200x500x 1,5 mm - Art. 81 272

1200x500x 2,0 mm - Art. 81 273

1200x500x 2,5 mm - Art. 81 274

sheet size:	approx. 1.200 x 500 mm
fibre-orientation:	90°C
activation time:	approx. 2 minutes (thickness 0,8 to 1,5 mm) at 120°C in a convection oven approx. 4 minutes (thickness 2,0 to 2,5 mm) at 140°C to 160°C in a convection oven
applications:	<ul style="list-style-type: none">• insole-stiffenings• rigidus-springs• above all for two-dimensional applications• higher stiffness in longitudinal direction (1.200 mm)
properties and benefits:	<ul style="list-style-type: none">• high power intake at little at dead weight• excellent construction-options• little material waste proportion• large-scale